

S1141

(ANSI:FR-4)UV Blocking

特点

- UV Blocking 和 AOI兼容，可提高PCB生产效率。
- 优良的耐热性。
- 优良尺寸稳定性。
- 优秀的机械性能和电性能。

FEATURES

- UV Blocking and AOI compatible, so as to Increase productivity.
- Good soldering reliability .
- Good dimensional stability.
- Excellent mechanical and electrical properties.

应用领域

电脑、仪器仪表、摄象机、通讯设备、电子游戏机等。

APPLICATIONS

Computer, Instrumentation, VCR, Communication equipment, Electronic game machine, etc.

GENERAL PROPERTIES

Test Item	Treatment Condition	Unit	Property Data	
			SPEC	Typical Value
Tg	DSC		130	140
Flammability	C-48/23/50	-	V-0	V-0
	E-24/125			
Volume Resistivity	After moisture resistance	M -cm	10 ⁶	5 × 10 ⁸
	E-24/125		10 ³	5 × 10 ⁶
Surface Resistance	After moisture resistance	M	10 ⁴	5 × 10 ⁷
	E-24/125		10 ³	5 × 10 ⁶
Arc Resistance	D-48/50+D-0.5/23	S	60	120
Dielectric Breakdown	D-48/50+D-0.5/23	KV	40	60
Dielectric Constant (1MHz)	C-24/23/50	-	5.4	4.6
Dissipation Factor (1MHz)	C-24/23/50	-	0.035	0.015
Thermal Stress	Unetched	-	No delamination	No delamination
	Etched			
Peel Strength	1oz	N/mm	1.05	1.8
	Cu. Foil		125	0.70
Flexural Strength	LW	MPa	415	600
	CW		345	500
Water Absorption	D-24/23	%	0.35	0.15
CTE Z-axis	Before Tg	TMA	μ m/m	55
	After Tg	TMA	μ m/m	260
CTI	IEC-112 Method	V	-	175

Specimen Thickness:1.6mm

Explanations: C = Humidity conditioning;
D = Immersion conditioning in distilled water;
E = Temperature conditioning.

The figures following the letter symbols indicate with the first digit the duration of the preconditioning in hours, with the second digit the preconditioning temperature in and with the third digit the relative humidity.

